



Asian Institute of Technology

Asian Center for Soil Improvement and Geosynthetics (ACSIG)
School of Engineering and Technology (SET)

Postal Address:
P.O. Box 4
Klong Luang,
Pathumthani 12120
Thailand

Street Address:
Km. 42 Phaholyothin Highway
Klong Luang
Pathum Thani 12120
Thailand

(For local calls, dial 02 before the
tel/fax nos.)
Tel: (66-2)524-5505
Tel: (66-2)524-5501
Tel: (66-2)524-5523
Fax: (66-2)524-6059
e-mail gtelab.ait.mail@gmail.com
http://www.ait.ac.th

LABORATORY TESTS ON CONSTRUCTION SAFETY-NET

Issued to: **TEMCO., LTD.**
Address: 8th Floor, Thaniya Bldg.,
62 Silom Road, Suriyawong, Bangrak,
Bangkok, 10500 Thailand
Sample description: **Polyester Safety Net 15x15 mm. (T-2018)**
Date Tested: 6 August 2018
Date Submitted: 8 August 2018
Testing Atmosphere: $23 \pm 2^\circ\text{C}$ temperature and $65 \pm 5\%$ humidity

Test Method: **ASTM D638**


Test Results:

Properties	Unit	Measure Tensile Strength			
		Trial 1	Trial 2	Trial 3	Mean
Tensile Strength	kgf per strand	36.6	32.6	34.5	34.6

DISCLAIMER :

TEMCO., LTD. is hereby forewarned that this report covers only the results of the Construction Safety Net sample that was received and tested according to the specified ASTM test standards and testing atmosphere of $23 \pm 2^\circ\text{C}$ temperature and $65 \pm 5\%$ humidity. This certificate, however, may not represent the condition of other products with the same nomenclature. This certificate will be kept in the active file for six months after which it will be disposed.

Submitted by:


Ms. Terdkiad Nontapot
Manager, ACSIG
Asian Institute of Technology


Dr. Kuo-Chieh Chao
Director, ACSIG
Asian Institute of Technology



Asian Institute of Technology

Asian Center for Soil Improvement and Geosynthetics (ACSIG)
School of Engineering and Technology (SET)

Postal Address:
P.O. Box 4
Klong Luang,
Pathumthani 12120
Thailand

Street Address:
Km. 42 Phaholyothin Highway
Klong Luang
Pathum Thani 12120
Thailand

(For local calls, dial 02 before the
tel/fax nos.)

Tel: (66-2)524-5505
Tel: (66-2)524-5501
Tel: (66-2)524-5523
Fax: (66-2)524-6059
e-mail gtelab.ait.mail@gmail.com
<http://www.ait.ac.th>

LABORATORY TESTS ON CONSTRUCTION SAFETY-NET

Issued to: **TEMCO., LTD.**
Address: 8th Floor, Thaniya Bldg.,
62 Silom Road, Suriyawong, Bangrak,
Bangkok, 10500 Thailand
Sample description: **Polyester Safety Net 15x15 mm. (T-2018)**
Date Tested: 6 August 2018
Date Submitted: 8 August 2018
Testing Atmosphere: $23 \pm 2^{\circ}\text{C}$ temperature and $65 \pm 5\%$ humidity

Test Method: ASTM D638


Test Results:


Properties	Unit	Measure Tensile Strength			
		Trial 1	Trial 2	Trial 3	Mean
Tensile Strength	kgf per strand	36.6	32.6	34.5	34.6

DISCLAIMER :

TEMCO., LTD. is hereby forewarned that this report covers only the results of the Construction Safety Net sample that was received and tested according to the specified ASTM test standards and testing atmosphere of $23 \pm 2^{\circ}\text{C}$ temperature and $65 \pm 5\%$ humidity. This certificate, however, may not represent the condition of other products with the same nomenclature. This certificate will be kept in the active file for six months after which it will be disposed.

Submitted by:


Ms. Terdkiad Nontapot
Manager, ACSIG
Asian Institute of Technology


Dr. Kuo-Chieh Chao
Director, ACSIG
Asian Institute of Technology

